



ADHESIVES & COATINGS
High Performance Compounds For Industry

ECA-375 Epoxy Hardener

100:15 Mix Ratio

Description:

ECA-375 imparts heat resistant characteristics together with very good chemical resistance with cure at ambient or elevated temps. This product has low viscosity, high reactivity and has been used extensively in the manufacture of compression molded water skis and wakeboards.

Advantages:

- High Chemical Resistance
- Low Viscosity.
- 100:15 mix ratio by weight.
- Rapid Cure.

Physical Properties:

<u>Property</u>	<u>Method</u>	<u>Value</u>	
Mix ratio	Weight	Resin 100	Hardener 15
Color	Visual	Straw	
Viscosity @ 77°F (cps)	Brookfield	100-200	
Pot Life (150gm 77°F)		15 Minutes	
Density	Weight/gal	8.65	

Quality Controlled Manufacturers of INKS, COATINGS, ADHESIVES, & MOLDING VINYLs and EPOXIES

Recommendations for the use of this product are based on tests believed to be reliable. However, since the use of this product is beyond our control, no guarantee or warranty of any kind express or implied is made with respect to information presented and QCM Co. assumes no responsibility for the results of the use of this product and processes described.

930 Central Ave. S. • Kent, WA 98032 • 1 (800) 321-0170 • (253) 859-0933 • Fax (253) 859-0935

www.qcminks.com • www.qcminds.com